

LENMAR™

FINE WOOD FINISHES



High Solids Water White CV • MegaSpeed Catalyzed Lacquers
White Catalyzed Topcoats • White Catalyzed Undercoaters

MegaVar™ Clear Topcoats

Lenmar offers three premium qualities of clear two-component catalyzed finishes. MegaSpeed, 1M.330X series, Catalyzed Lacquer, is a superior quality two component finish, which has a three-day potlife, and surprising chemical resistance. MegaVar, 1M.430X series, Conversion Varnish, is a proven benchmark for varnishes in the marketplace with even higher solids than the MegaSpeed product. The MegaVar CV offers an easy-to-apply solution to two component finishing while achieving a durable, resistant, long-lasting film. MegaVar Plus, 1M.530X line, is Lenmar's ultimate high solids two-component finish. With solids over 50%, yet achieving excellent flow and leveling on application, this product is capable of surpassing KCMA standard in two coats on most substrates. It provides the maximum available chemical and moisture resistance from two-component, conversion varnish technology.



MegaVar™ White Finishes

Lenmar's pigmented two-component finishing system consists of the MegaVar 1S.750, white conversion undercoater, and the MegaVar 1S.75X line of white conversion topcoats. The 1S.750 undercoater, at over 60% solids, is ideal for the filling of MDF or open pore substrates, and even though high in solids, this product, under normal conditions, is ready to sand in 25-30 minutes. When used in combination with any of the four available sheens in the 1S.75X series, this system will surpass KCMA requirements in two coats. The MegaVar 1S.75X series of white topcoats is easy to apply, and provides a moisture and chemically resistant finish with exceptional durability.

MegaVar™ Sealers

While all of Lenmar's clear conversion varnishes are capable of application as a self-sealing finish, Lenmar offers a two-component sealer for finishers who would prefer a more traditional system. Lenmar's 1C.5300, Catalyzed Sealer, is compatible with all of the MegaVar topcoat systems, and may be easily used to seal the wood surface and obtain a strong, stable base for whichever catalyzed system is used to complete the finish. The MegaVar 1C.5300 Catalyzed Sealer is Lenmar's highest solids sealer, and performs equal to the expectation of that position, with quick drying times and exceptional sanding characteristics.



Code#	Product Description	Glosses Available	Catalyst (% / oz per gal)		Solids (by Wt)	VOC (g/L)	Viscosity (#2 Zahn)	Recoat	Clean-up	Dry Color	Flash Point
			1A.622B	1A.5300B							
1M.530X	MegaVar™ +Plus High Solids WW CV	90+, 60, 40, 20	4% / 5 oz	8% / 10 oz	50%	<550	Yes	15-20"	30-45 Min	Lac Thinner	WW 41
1M.430X	MegaVar™ Premium WW CV	90+, 60, 40, 20, 10	3% / 4 oz	6% / 8 oz	40%	<600	Yes	26-28"	30-45 Min	Lac Thinner	WW 39
1M.330X	MegaSpeed High Solids WW Cat Lac	90+, 60, 40, 20, 10	2.5% / 3 oz	5% / 6 oz	36%	<600	Yes	20-25"	25-35 Min	Lac Thinner	WW 35
1C.5300	MegaVar™ Quick Dry Catalyzed Sealer	n/a	3% / 4 oz	6% / 8 oz	38%	<600	Yes	20-22"	25-35 Min	Lac Thinner	WW 35
1S.75X	MegaVar™ White Catalyzed Topcoat	80+, 60, 40, 20	3% / 4 oz	6% / 8 oz	48%	<550	Yes	42-48"	30-45 Min	Lac Thinner	White 28
1S.750	MegaVar™ White Catalyzed Undercoater	n/a	4.5% / 6 oz	9% / 12 oz	65%	<450	Yes	26-32" (EZ5)	25-35 Min	Lac Thinner	White 41

LENMAR™
FINE WOOD FINISHES

4701 O'Donnell Street Baltimore, Maryland 21224 Toll Free: 800-966-7020 www.lenmar-coatings.com